

## Foamkore Technical Guide

*Foamkore is a balanced constructed panel that provides a structural panel with greatly reduced weight*

Patent #5,618,601; #5,232,762; #5,824,382

### Fabricating Techniques

#### Product Description


Foamkore is a balanced constructed panel that provides a structural panel with greatly reduced weight. It consists of a polystyrene foam core and thin face materials.

#### Product Characteristics

Foamkore is constructed by capturing a polystyrene foam core with higher density face panels to provide a strong lightweight panel with structural integrity. Two core materials are available in this product. One is an extruded polystyrene foam (XPF) that is closed cell in structure and provides a consistent and uniform surface to machine. The other product is expanded polystyrene foam (EPF) with a slightly lower density. The sandwich panel construction method incorporates the use of thinner outer panels bonded to a thicker lighter core. This construction provides for a strong light panel that can be compared to a truss beam. This panel concept is to space thin stronger face panels apart with a thicker core to ensure the combination will be stiff and strong.

#### Attachment Methods

The rigid face materials used in the Foamkore product provide the ability to use conventional attachment methods. The use of glue, staples, nails, screws and other similar fasteners will allow the panel to be physically and structurally attached to other materials. The big advantage with Foamkore is the reduced weight from 50-80% from conventional panels. This reduced weight will allow for usages where



Box Corner View Attachment



Box Cut Away View



Edge Treatment - Inside Lumber Band



Edge Treatments



Edge Treatment Veneer Band



Edge Lumber Band

# Richelieu

heavier panels would be prohibited. Foamcore is appropriate for use in areas that weight is a concern.

## Fire Rating

The extruded polystyrene core has been ASTM E84 tested with results of 5-10 Flame Spread and 60-200 smoke development which falls in a Class A qualification. However, the addition of the face materials must be taken into consideration for overall fire rating.

## Edge Treatments

Many edging options are possible with the Foamcore.

## Edge Capture

The adjoining panels or rails can capture the panel. This is done in the exhibit industry by the use of extruded plastic or aluminum rails. This can be a structure part of just a U channel to cover the edge.

## Edge Insert

The edge of a panel can be machined to accept a wooden insert. This insert can be held in place with glue or pinned until the glue is cured. Outer Edge Band: A wooden outer band can be glued to the Foamcore by use of a wood PVC glue. This will allow for more edge machining options.

## Edgebanding

An edgeband can be applied by use of an automated edgebander or by hand with a contact or PVA adhesive. When using automated edgebanding equipment proper adjustments and test should be made to provide the desired results. Contact adhesives developed for polystyrene foam are required.

## Corner Post

The ability to remove a small area of the core and one side allows for the attachment by glue and nails a wooden strip to serve as a post to provide the means to attach panels with other material.



Euro Hinge Alternate Views



Inside Corner Post Joint



Inside Corner Post Miter Joint



Corner Fastener

## **Laminating Methods**

Most face materials can be easily adhered to the Foamkore panels. The use of contact adhesive is advisable where possible. It is possible to cold or hot press material but minimum pressure should be used. A pressure of 10-15psi is usually suitable for these applications. An actual test should be used to determine what is best suited for the material you may want to laminate. Also it is important to remember that Foamkore is balanced constructed panel and the need to keep it stable may require equal material to be applied to both sides.

## **Conditioning and Storage**

Proper storage is extremely important with Foamkore. The balanced constructed panel should be stored on a flat uniform surface away from direct contact with the floor to allow for air circulation. A cover sheet is recommended to maintain uniform moisture levels. Some weight is desired to keep the cover sheet tight during storage. If panels must be stored in a vertical position make sure this is done without excessive weight to either side.

## **Moisture Resistance**

In most applications Foamkore is a moisture resistant material. The core material provides an outstanding moisture resistance to water. The face panels are laminated with moisture resistant glue leaving only the face susceptible to moisture. In tests, all the plywood face materials have performed extremely well.